

Alltek Cachet Bleu ZS

READY MIXED PLASTER

MACHINE APPLICATION

INTERIOR APPLICATION



DESCRIPTION

Alltek Blue Label Skim ZS is a ready-for-use cream plaster, with fillers (fine calcium carbonate), organic binders and additives (application improvers, preservative and rust inhibitor).

USE

- Plaster for interiors, walls and ceilings on all standard substrates.
- Due to its exceptional adhesive properties, Alltek Cachet Bleu ZS can be sprayed directly onto concrete.
- Smooth finish after smoothing and sanding.

TECHNICAL SPECIFICATIONS



TYPICAL SPREADABILITY

0.8 to 2 kg/m² per layer depending on smoothness of substrate.



DENSITY

1.7 +/- 0.1 kg/l



SOLID CONTENT

- Solid content by mass: 76%
- Solid content by volume: 60%



APPLICATION CONDITIONS

- +8°C to +35°C
- Max. relative humidity 70%



PH

8 +/- 1



CLEANING TOOLS

With water



DRYING

- 24 h on average, depending on application thickness, temperature, ventilation, humidity and substrate type. Sanding and recoating: after complete drying.



RECOMMENDED THICKNESSES

- Min. thickness: 0,4 mm
- Max. thickness: 2 mm

CHARACTERISTICS

- Ready to use
- Easy to apply.
- Outstanding filling and finish.
- Excellent adhesive properties.
- Very good spreading power.
- Easily sanded.
- Can be mixed with our orange label plaster for an even finer finish.
- Fire rating: A2-s1, d0 as per European standard EN 13501-1.
- Classification: group III class 2 as per the standard AFNOR NF T 36-005, in compliance with the standard AFNOR NF T 30-608

PACKAGING AND STORAGE

- 25kg plastic bag with handle
- Shelf life is 1 year in unopened original packaging, protected from frost and extreme heat.

ENVIRONMENTAL INFORMATION

- VOC content: < 1 g/l.

- Indoor Air Emission Class



*Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

METHOD OF APPLICATION

SUBSTRATES:

- Poured concrete, rough concrete.
- Terracotta bricks and tiles, plaster, gypsum blocks, plasterboard.
- Wood and wood products, old painted substrates in good condition

PREPARATION OF SUBSTRATE:

- The substrates, preparatory work and application conditions must be compliant with applicable building trade regulations (e.g. DTU) and standards.

APPLICATION TIPS:

- Stir before use if necessary.
- Spraying machine nozzle 4 to 8 mm, depending on condition of substrate and equipment used (follow the manufacturer's advice).
- Smoothing blades of all sizes.
- Sanding with grain size 100 to 150.

RECOMMENDATIONS:

- Ensure adequate ventilation to remove excess moisture and accelerate drying.

HEALTH AND SAFETY

The safety information sheet is available from: www.icp-alltek.com/en-gb/documentation/