



Alltek Cachet Vert

READY MIXED PLASTER

MACHINE APPLICATION

INTERIOR APPLICATION



DESCRIPTION

Alltek Cachet Vert is an off-white plaster based on natural mineral fillers, with an organic binder and additives.

USE

- Plaster for interiors, walls and ceilings on all standard substrates.
- Ready filling and smoothing mixed plaster for remove surface irregularities before applying the skimming coat.
- Direct application to aerated concrete, rough concrete.

TECHNICAL SPECIFICATIONS



TYPICAL SPREADABILITY

3 to 6 kg/m² per layer depending on smoothness of substrate.



DENSITY

1.7 +/- 0,1 kg/l



SOLID CONTENT

- Solid content by mass: 77%
- Solid content by volume: 61%



APPLICATION CONDITIONS

- +8°C to +35°C
- Max. relative humidity 70%



PH

8 +/- 1



CLEANING TOOLS

With water



DRYING

- 24 to 36 h on average, depending on application thickness, temperature, ventilation, humidity and substrate type. Sanding and recoating: after complete drying.



RECOMMENDED THICKNESSES

- Min. thickness: 1 mm
- Max. thickness: 4 mm

CHARACTERISTICS

- Ready to use
- Excellent filling power.
- Fire rating: A2-s1, d0 as per European standard EN 13501-1.
- Classification: group III class 2 as per AFNOR NF T 36-005, in compliance with the standard AFNOR NF T 30-608.

PACKAGING AND STORAGE

- 25kg plastic bag with handle
- Shelf life is 1 year in unopened original packaging, protected from frost and extreme heat.

ENVIRONMENTAL INFORMATION

- VOC content: < 1 g/l.

- Indoor Air Emission Class



*Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

METHOD OF APPLICATION

SUBSTRATES:

- Concrete, aerated concrete and all standard substrates, old and new.

PREPARATION OF SUBSTRATE:

- The substrates, preparatory work and application conditions must be compliant with applicable building trade regulations (e.g. DTU) and standards.

APPLICATION TIPS:

- Stir before use.
- Spraying machine with 4-6 mm nozzles.
- Sanding with grain 80 to 100.

RECOMMENDATIONS:

- Ensure adequate ventilation to remove excess moisture and accelerate drying.

HEALTH AND SAFETY

The safety information sheet is available from:
www.icp-alltek.com/en-gb/documentation/